



## PHOENIX RESIN Co.,Ltd.

ADD : No. 8 floor, SHP Plaza Building - No. 12 Lach Tray Str, Ngo Quyen Dist, Hai Phong City

Tel : +84 - 225.3835710 Fax: +84 - 225.3571053

Hotline : +84 - 91 2106467

Name of product	Clarity	Solvent	Color (Gardner)	Viscosity	Non-Volatile Content	Specific Gravity	OH Value	Tg °C	Description	Typical applications
<b>ACRYPHOENIX 4350</b>	Clear, free of particles	n-BA	< 2	Z2-Z4	50	0.98÷1.02	43	45	Excellent Pigment Dispersion, Excellent Fast Drying, Good Chemical Resistance and Good Hardness	Used for Industrial Top Coating and Color Base Coat
<b>ACRYPHOENIX 5099</b>	Clear, free of particles	Toluene, BC	< 2	Z3-Z5	50	0.98÷1.02		76	Excellent Fast Drying, Good Chemical Resistance and Good Hardness.	Used For Middle Coat for Plastic
<b>ACRYPHOENIX 6650</b>	Clear, free of particles	n-BA	< 2	Z4-Z5	52	0.98÷1.02	66	53	Excellent Pigment Dispersion, Excellent Fast Drying, Good Chemical Resistance and Good Hardness	Used for Industrial Top Coating and Color Base Coat
<b>ACRYPHOENIX 10259</b>	Clear, free of particles	Xylene, PMA, n-BA	< 2	Z2-Z4	59	1.01÷1.05	102	63.5	High Gloss, Excellent Fast Drying, Good Chemical Resistance and Good Hardness.	Used for Industrial Top Coating and Plastic Top Coating
<b>ACRYPHOENIX 40911</b>	Clear, free of particles	n-BA, n-BuOH, EA	< 2	Z5,(Z6 – Z7)	40	0.95÷0.99		71	Excellent Fast Drying, Good Chemical Resistance and Good Adhesion.	Used for Under Coat for Plastic
<b>ACRYPHOENIX 2101</b>	Clear, free of particles	n-BA, Xylene, Toluene, PMA	< 2	Z5,(Z6 – Z7)	60		16	39	Has high gloss and is weather resistant, dries quickly	Good adhesion on galvanized steel