



PHOENIX RESIN Co.,Ltd.

ADD : No. 8 floor, SHP Plaza Building - No. 12 Lach Tray Str, Ngo Quyen Dist, Hai Phong City

Tel : +84 - 225.3835710 Fax: +84 - 225.3571053

Hotline : +84 - 91 2106467

Name of product	Oil type	Oil content	Non-volatile content	Viscosity	Acid value	OH Value	Color	Description	Typical applications
Very long oil									
ALKYPHOENIX T74 - 100LV	SOFA	74	97-100	A-E	max 3		max 6		Thermoplastic road marking paint
ALKYPHOENIX S77 - 100LV	SOFA	77	97-100	U-X	<10		max 6		Thermoplastic road marking paint
Long oil									
ALKYPHOENIX SF60 - 80WS	Soya oil	60	80	Z7-Z8	max 10		max 6	Good gloss and low yellowing	House paints and decorative paints, steel construction, marine paints
ALKYPHOENIX S60 - 80HV	Soya oil	60	80	>Z10	<10		max 6	Good gloss and low yellowing	House paints and decorative paints, steel construction, marine paints
ALKYPHOENIX S60 -55	Soya oil	60	55	Z9-Z10	3_9		max 6	Good gloss and low yellowing	House paints and decorative paints, steel construction, marine paints
ALKYPHOENIX S63 - 70MV	Soya oil	63	70	Z5-Z6	3_9		max 6	Good gloss and low yellowing	House paints and decorative paints, steel construction, marine paints
ALKYPHOENIX S63 - 80	Soya oil	63	80	Z7-Z8	3_9		max 6	Good gloss and low yellowing	House paints and decorative paints, steel construction, marine paints
ALKYPHOENIX S63 - 80 HV	Soya oil	63	80	Z9-Z10	3_9		max 6	Good gloss and low yellowing	House paints and decorative paints, steel construction, marine paints
ALKYPHOENIX S63 - 80 MV	Soya oil	63	80	Z7-Z8	3_9		max 6	Good gloss and low yellowing	House paints and decorative paints, steel construction, marine paints
ALKYPHOENIX SF63 - 80	Soya oil	63	80	> Z10	< 10		max 6	Good gloss and low yellowing	House paints and decorative paints, steel construction, marine paints

Medium oil									
ALKYPHOENIX SR40 – 70	SOFA	40	70	Z5-Z6	max 10		max 5	excellent non-yellowing resistance, initial gloss .	Air drying architectural and decorative paints, structural steel and marine paints.
ALKYPHOENIX S40 – 70	SOFA	40	70	Z5-Z6	max 10		max 5	excellent non-yellowing resistance, initial gloss .	Air drying architectural and decorative paints, structural steel and marine paints.
Name of product	Oil type	Oil content	Non-volatile content	Viscosity	Acid value	OH Value	Color	Description	Typical applications
Short oil									
ALKYPHOENIX P32 – 70	Palm oil	32	70	Z7-Z8	max 10	130±10	max 3	Good gloss, very light color and fast drying	Top coat of wood coating and enamels
ALKYPHOENIX C31-70	Coconut oil	31	70	Z7-Z8	max 10	130±10	max 3	Very light color and fast drying	Top coat of wood coating and enamels
ALKYPHOENIX S3620-70	Mix vegetable oil	36	70	Y-Z	max 12	130±10	max 4	Good gloss and low yellowing	Base of wood coatings
ALKYPHOENIX S3010-70	SOFA	30	70	Y-Z2	max 10	110±10	max 3	Fast dry, harness and good sanding	Primer coat of wood coating and colored enamels
ALKYPHOENIX S3011-70	SOFA	30	70	Z1-Z3	max 12	120±10	max 3	High viscosity, good levelling, fast dry, good surface hardness & flexibility.	Primer and finhised of wood coating
ALKYPHOENIX S3070-80	Synthetic fatty acid	30	80	W-Z	max 12	150±15	max 1	Superior color and color retention properties	Top coat of premium wood coating and enamels